

PC Gebalon 15-141

PC

geba Kunststoffcompounds GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	2200	MPa	ISO 527
Yield stress	57	MPa	ISO 527
Yield strain	6.2	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	124	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	136	°C	ISO 75-1/-2
Vicat softening temperature, B	141	°C	ISO 306
Other properties			
Density	1200	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Applications

Automotive, Electrical and Electrical