

PC2500FR

PC

Shanghai Kumho Sunny Plastics Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	63	MPa	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Flexural Modulus	2200	MPa	ASTM D 790
Flexural Strength	85	MPa	ASTM D 790
Izod Impact notched, 1/8 in	600	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-1	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 264 psi	135	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E15	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1210	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	240 - 280	°C	-
Mold temperature	60 - 100	°C	-

Characteristics**Processing**

Injection Molding

Applications

Electrical and Electronical

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

Asia Pacific