

| Mechanical properties          | Value       | Unit | Test Standard |
|--------------------------------|-------------|------|---------------|
| <b>ISO Data</b>                |             |      |               |
| <sup>[C]</sup> Tensile Modulus | <b>2300</b> | MPa  | ISO 527       |
| <sup>[C]</sup> : CAMPUS        |             |      |               |

| Thermal properties   | Value                    | Unit        | Test Standard        |
|--|--------------------------|-------------|----------------------|
| <b>ISO Data</b>  |                          |             |                      |
| <sup>[C]</sup> Temp. of deflection under load, 1.80 MPa                  | <b>130</b>               | °C          | ISO 75-1/-2          |
| <sup>[C]</sup> Temp. of deflection under load, 0.45 MPa                  | <b>135</b>               | °C          | ISO 75-1/-2          |
| <sup>[C]</sup> Vicat softening temperature, B                            | <b>145</b>               | °C          | ISO 306              |
| <sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.<br>Thickness tested | <b>V-0</b><br><b>1.6</b> | class<br>mm | IEC 60695-11-10<br>- |
| <sup>[C]</sup> Burning Behav. at thickness h<br>Thickness tested         | <b>V-0</b><br><b>3.2</b> | class<br>mm | IEC 60695-11-10<br>- |
| <sup>[C]</sup> : CAMPUS  |                          |             |                      |

| Other properties        | Value       | Unit              | Test Standard |
|-------------------------|-------------|-------------------|---------------|
| <sup>[C]</sup> Density  | <b>1200</b> | kg/m <sup>3</sup> | ISO 1183      |
| <sup>[C]</sup> : CAMPUS |             |                   |               |

## Characteristics

### Special Characteristics

Flame retardant, U.V. stabilized or stable to weather

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa