

PGPC-1822

PC

Persian Gulf Petrochemical Industry Commercial Co.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	20.1	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mechanical properties			
ASTM Data			
Tensile Modulus	2200	MPa	ASTM D 638
Tensile Strength at Yield	60	MPa	ASTM D 638
Elongation at Break	80	%	ASTM D 638
Thermal properties			
ASTM Data			
Vicat Temperature	142	°C	ASTM D 1525
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	20	kV/mm	ASTM D 149
Optical properties			
ASTM Data			
Light Transmittance	80	%	ASTM D 1003
Other properties			
Density	1200	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

Near East/Africa

Applications

Automotive, Electrical and Electronical, Sports Equipment