

**PRL PC-FD4**

PC

Polymer Resources, Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>24</b>	g/10min	ASTM D 1238
Temperature	<b>300</b>	°C	-
Load	<b>1.2</b>	kg	-
Mold Shrinkage, MD	<b>0.006</b>	mm/mm	ASTM D 955
Mold Shrinkage, TD	<b>0.006</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>62.1</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>65.5</b>	MPa	ASTM D 638
Elongation at Yield	<b>6</b>	%	ASTM D 638
Elongation at Break	<b>120</b>	%	ASTM D 638
Flexural Modulus	<b>2275</b>	MPa	ASTM D 790
Flexural Strength	<b>92.4</b>	MPa	ASTM D 790
Rockwell Hardness	<b>M70</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>641</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>129</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>124</b>	°C	ASTM D 648
Vicat Temperature	<b>141</b>	°C	ASTM D 1525
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	<b>1</b>	%	ASTM D 1003
Light Transmittance	<b>88</b>	%	ASTM D 1003
<b>Other properties</b>			
Density	<b>1200</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>118 - 124</b>	°C	-
Pre-drying - Time	<b>3 - 4</b>	h	-
Melt temperature	<b>266 - 293</b>	°C	-
Mold temperature	<b>65.6 - 93.3</b>	°C	-
Zone 1	<b>249 - 271</b>	°C	-
Zone 2	<b>260 - 282</b>	°C	-
Zone 3	<b>271 - 293</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Certifications**

Food contact

**Delivery form**

Pellets

**Applications**

General Purpose

**Special Characteristics**

High impact or impact modified

**Regional Availability**

North America