

PRL PC-FR3-D-(color)-3

PC

Polymer Resources, Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	17	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	62.1	MPa	ASTM D 638
Tensile Strength at Break	55.2	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Elongation at Break	90	%	ASTM D 638
Flexural Modulus	2206	MPa	ASTM D 790
Flexural Strength	89.6	MPa	ASTM D 790
Rockwell Hardness	M70	-	ASTM D 785
Izod Impact notched, 1/8 in	641	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	135	°C	ASTM D 648
DTUL @ 264 psi	129	°C	ASTM D 648
Vicat Temperature	149	°C	ASTM D 1525
Electrical properties			
ISO Data			
Comparative tracking index	325	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	22.8	kV/mm	ASTM D 149
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Arc Resistance	150	s	ASTM D 495
Other properties			
Density	1210	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	118 - 124	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	282 - 310	°C	-
Mold temperature	71.1 - 93.3	°C	-
Zone 1	266 - 288	°C	-
Zone 2	277 - 299	°C	-
Zone 3	288 - 310	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant, U.V. stabilized or stable to weather

Delivery form

Pellets

Regional Availability

North America

Additives

Flame retarding agent