

**PRL PC-GP2-D**

PC

Polymer Resources, Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	12.5	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	62.1	MPa	ASTM D 638
Tensile Strength at Break	68.9	MPa	ASTM D 638
Elongation at Yield	6.5	%	ASTM D 638
Elongation at Break	140	%	ASTM D 638
Flexural Modulus	2310	MPa	ASTM D 790
Flexural Strength	95.8	MPa	ASTM D 790
Rockwell Hardness	M70	-	ASTM D 785
Izod Impact notched, 1/8 in	801	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	135	°C	ASTM D 648
DTUL @ 264 psi	129	°C	ASTM D 648
Vicat Temperature	152	°C	ASTM D 1525

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Comparative tracking index	325	-	IEC 60112
<b>ASTM Data</b>			
Dielectric Strength, Short Time	28	kV/mm	ASTM D 149
Volume Resistivity	1E15	Ohm*cm	ASTM D 257
Arc Resistance	150	s	ASTM D 495

Optical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Haze	1	%	ASTM D 1003
Light Transmittance	88	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	1200	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	118 - 124	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	288 - 316	°C	-
Mold temperature	71.1 - 93.3	°C	-
Zone 1	271 - 293	°C	-
Zone 2	282 - 304	°C	-
Zone 3	293 - 316	°C	-

**Characteristics****Processing**

Injection Molding

**Applications**

General Purpose

**PRL PC-GP2-D**

PC

Polymer Resources, Ltd.

**Delivery form**

Pellets

**Regional Availability**

North America

**Special Characteristics**

High impact or impact modified