

**PRL PC-HH-UV**

PC

Polymer Resources, Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>3.5</b>	g/10min	ASTM D 1238
Temperature	<b>300</b>	°C	-
Load	<b>1.2</b>	kg	-
Mold Shrinkage, MD	<b>0.007</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile Strength at Yield	<b>66.2</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>74.5</b>	MPa	ASTM D 638
Flexural Modulus	<b>2137</b>	MPa	ASTM D 790
Flexural Strength	<b>96.5</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>374</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
DTUL @ 66 psi	<b>154</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>146</b>	°C	ASTM D 648
<b>Other properties</b>			
<b>ASTM Data</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1190</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
<b>ASTM Data</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>121 - 129</b>	°C	-
Pre-drying - Time	<b>3 - 4</b>	h	-
Melt temperature	<b>316 - 343</b>	°C	-
Mold temperature	<b>76.7 - 98.9</b>	°C	-
Zone 1	<b>299 - 338</b>	°C	-
Zone 2	<b>299 - 338</b>	°C	-
Zone 3	<b>327 - 371</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Regional Availability**

North America