

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	62.1	MPa	ASTM D 638
Flexural Modulus	2290	MPa	ASTM D 790
Izod Impact notched, 1/8 in	750	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	135	°C	ASTM D 648
DTUL @ 264 psi	124	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1210	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	3 - 6	h	-
Melt temperature	282 - 299	°C	-
Mold temperature	71 - 93	°C	-
Zone 1	260 - 282	°C	-
Zone 2	271 - 293	°C	-
Zone 3	282 - 304	°C	-
Nozzle temperature	277 - 299	°C	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets, Natural Color

**Special Characteristics**

Flame retardant, High impact or impact modified, U.V. stabilized or stable to weather

**Regional Availability**

North America