

**RamTough PZ507WT155**

PC

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>16</b>	g/10min	ISO 1133
Temperature	<b>300</b>	°C	-
Load	<b>1.2</b>	kg	-
<b>Other Standards<sup>[S]</sup></b>			
Molding shrinkage, parallel	<b>0.3</b>	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>2400</b>	MPa	ISO 527
Tensile Strength	<b>62</b>	MPa	ISO 527
Yield strain	<b>6</b>	%	ISO 527
Izod notched impact strength, +23°C	<b>11</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	<b>820</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-
Glow Wire Flammability Index (GWFI)	<b>960</b>	°C	IEC 60695-2-12
GWFI - thickness tested (1)	<b>1.6</b>	mm	-

Other properties	Value	Unit	Test Standard
Humidity absorption	<b>0.35</b>	%	Sim. to ISO 62
Density	<b>1220</b>	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>120</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Mold temperature	<b>80 - 120</b>	°C	-
Feed temperature	<b>60 - 70</b>	°C	-
Zone 1	<b>220 - 230</b>	°C	-
Zone 2	<b>230 - 250</b>	°C	-
Zone 3	<b>250 - 260</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

White

**Special Characteristics**

Flame retardant, U.V. stabilized or stable to weather

**Certifications**

RoHS compliant

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa