

RamTough RZ222WT131

PC

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	16.5	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	2200	MPa	ISO 527
Tensile Strength	60	MPa	ISO 527
Yield strain	5.6	%	ISO 527
ASTM Data			
Izod Impact notched, 1/8 in	700	J/m	ASTM D 256
Other properties			
Density	1200	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.02	%	-
Mold temperature	80 - 120	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	230 - 240	°C	-
Zone 2	240 - 260	°C	-
Zone 3	260 - 270	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

White

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa