

| Mechanical properties | Value | Unit | Test Standard |
|-----------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength | 110 | MPa | ASTM D 638 |
| Elongation at Break | 2.5 | % | ASTM D 638 |
| Flexural Modulus | 7810 | MPa | ASTM D 790 |
| Flexural Strength | 179 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 100 | J/m | ASTM D 256 |

| Electrical properties | Value | Unit | Test Standard |
|-----------------------|--------|------|---------------|
| ASTM Data | | | |
| Surface Resistivity | 100000 | Ohm | ASTM D 257 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 1240 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Injection Molding

Special Characteristics

Increased electrical conductivity

Delivery form

Black

Regional Availability

North America