

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	70	MPa	ASTM D 638
Flexural Modulus	2040	MPa	ASTM D 790
Flexural Strength	100	MPa	ASTM D 790
Rockwell Hardness	R 122	-	ASTM D 785
Izod Impact notched, 1/8 in	785	J/m	ASTM D 256
Thermal properties			
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	1.0	mm	-
Yellow Card available	yes	-	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1	mm	-
DTUL @ 264 psi	127	°C	ASTM D 648
Optical properties			
ASTM Data			
Haze	2	%	ASTM D 1003
Light Transmittance	88	%	ASTM D 1003
Other properties			
Density	1200	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Flame retardant, U.V. stabilized or stable to weather,
Transparent

Regional Availability

Asia Pacific