

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	26	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
ASTM Data			
Tensile Strength	60	MPa	ASTM D 638
Flexural Modulus	2350	MPa	ASTM D 790
Flexural Strength	104	MPa	ASTM D 790
Rockwell Hardness	R 121	-	ASTM D 785
Izod Impact notched, 1/8 in	500	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	124	°C	ASTM D 648
Vicat Temperature	146	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 130	°C	-
Pre-drying - Time	4 - 8	h	-
Melt temperature	260 - 290	°C	-
Mold temperature	80 - 100	°C	-
Injection pressure	5 - 8	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

White

Special Characteristics

Flame retardant, Halogen-free

Regional Availability

Asia Pacific