

**Product Texts**

Metal substitution.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>1.0</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>1.3</b>	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>4000</b>	MPa	ISO 527
Yield stress	<b>100</b>	MPa	ISO 527
Yield strain	<b>20</b>	%	ISO 527
Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>4</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>343</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>150</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water absorption	<b>0.45</b>	%	Sim. to ISO 62
Density	<b>1290</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>120 - 150</b>	°C	-
Pre-drying - Time	<b>3 - 5</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>355 - 375</b>	°C	-
Mold temperature	<b>170 - 200</b>	°C	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Delivery form**

Natural Color

**Regional Availability**

Europe