

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8800	MPa	ISO 527
Tensile Strength	92	MPa	ISO 527
Strain at break	4	%	ISO 527
Charpy impact strength, +23°C	44	kJ/m ²	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	143	°C	ISO 11357-1/-2

Electrical properties	Value	Unit	Test Standard
Other Standards^[5]			
Volume resistivity	1.4E14	Ohm*m	IEC 61340-2-3
Surface resistivity	4.2E15	Ohm	IEC 61340-2-3

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1440	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	140 - 160	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	390 - 400	°C	-
Mold temperature	160 - 210	°C	-
Zone 1	360 - 400	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, White

Regional Availability

North America, Europe, Asia Pacific, South and Central America