

**Product Texts**

**Natural colored polyether ether ketone for dental applications**

VESTAKEEP® D4 G is natural colored, high viscosity polyether ether ketone (PEEK) that is especially designed for removable and fixed dentures, crowns and bridges.

**Biocompatibility of VESTAKEEP® Dental**

For VESTAKEEP® D4 G, biocompatibility has been tested following ISO 10993-1 recommendations for permanent mucous membrane contact.

The composition is optimised for high biocompatibility and superior mechanical, thermal and chemical resistance.

**Biocompatibility test reports available for VESTAKEEP® D4 G**

Standard	Description
ISO 10993-03	Genotoxicity: Salmonella Typhimurium Reverse Mutation Test (Ames Test)
ISO 10993-05	Cytotoxicity: Quantitative Growth Inhibition Test
ISO 10993-10	Irritation: Intracutaneous Reactivity
ISO 10993-10	Sensitization: Local Lymph Node Assay
ISO 10993-11	Acute Systemic Toxicity
ISO 10993-11	Subacute / Subchronic Toxicity 14 days
ISO 10993-18	Extraction Tests
USP Class VI	Acute Systemic Toxicity Intracutaneous Reactivity Muscle Implantation

**Processing of VESTAKEEP® Dental**

VESTAKEEP® D4 G can be processed by common melt processing techniques like injection molding and extrusion. For injection molding, we recommend melt temperatures in the 380°C to 400°C range. The mold temperature should be within 160°C to 200°C, preferably 180°C.

**Delivery of VESTAKEEP® Dental**

VESTAKEEP® D4 G is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT [EVONIK-HP@EVONIK.COM](mailto:EVONIK-HP@EVONIK.COM)  
OR VISIT OUR PRODUCT AT [WWW.EVONIK.COM/MEDICAL-TECHNOLOGY](http://WWW.EVONIK.COM/MEDICAL-TECHNOLOGY)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	12	cm <sup>3</sup> /10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	3500	MPa	ISO 527
<sup>[C]</sup> Yield stress	96	MPa	ISO 527
<sup>[C]</sup> Yield strain	5	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	8	kJ/m <sup>2</sup>	ISO 179/1eA

**VESTAKEEP® D 4 G**

PEEK

Evonik Operations GmbH

<sup>[C]</sup> Type of failure	C	-	-
<sup>[C]</sup> Charpy notched impact strength, -30°C	7	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Type of failure	C	-	-

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	340	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	153	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	155	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	210	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	305	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	45	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.4	%	Sim. to ISO 62
<sup>[C]</sup> Density	1300	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	380	°C	ISO 294
Injection Molding, mold temperature	180	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Delivery form**

Pellets, Natural Color

**Features**

Thermal Stability

**Chemical Resistance**

General Chemical Resistance

**Certifications**

Medical Grade, Biocompatibility ISO 10993, US Pharmacopeia Class VI Approved

**Applications**

Medical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa