

**LARPEEK 50 K/30**

PEEK-CF

LATI Industria Termoplastici S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	21500	MPa	ISO 527
Stress at break	225	MPa	ISO 527
Strain at break	1.5	%	ISO 527
Charpy impact strength, +23°C	45	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	6.5	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	300	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	300	°C	ISO 75-1/-2
Vicat softening temperature, B	300	°C	ISO 306
Coeff. of linear therm. expansion, parallel	5	E-6/K	ISO 11359-1/-2

Other properties	Value	Unit	Test Standard
Density	1400	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	3	h	-
Melt temperature	370 - 400	°C	-
Mold temperature	170 - 200	°C	-

**Characteristics****Processing**

Injection Molding

**Features**

Low Smoke

**Chemical Resistance**

General Chemical Resistance

**Regional Availability**

Europe