

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	12	cm <sup>3</sup> /10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	18500	MPa	ISO 527
Tensile Strength	185	MPa	ISO 527
Strain at break	1.3	%	ISO 527
Flexural modulus, 23°C	18400	MPa	ISO 178
Flexural strength	245	MPa	ISO 178
Charpy impact strength, +23°C	25	kJ/m <sup>2</sup>	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	143	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	325	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	340	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	7	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	38	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Volume resistivity	1200	Ohm*m	ISO 3915

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1400	kg/m <sup>3</sup>	ISO 1183
Bulk density	620	kg/m <sup>3</sup>	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	140 - 180	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	390 - 400	°C	-
Mold temperature	160 - 200	°C	-
Zone 1	360 - 400	°C	-

## Characteristics

### Processing

Injection Molding

### Features

Tribologic Grade

### Delivery form

Pellets, Black

### Applications

Automotive

**Additives**

Lubricants

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America