

RTP 2281 LF

PEEK-CF10

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	11720	MPa	ASTM D 638
Tensile Strength	186	MPa	ASTM D 638
Flexural Modulus	10340	MPa	ASTM D 790
Flexural Strength	262	MPa	ASTM D 790
Izod Impact notched, 1/8 in	74.7	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ASTM D 792
Moisture Content	0.1	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	3	h	-
Melt temperature	349 - 399	°C	-
Mold temperature	163 - 218	°C	-
Injection pressure	82.7 - 124	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific