

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	15000	MPa	ISO 527
Stress at break	175	MPa	ISO 527
Strain at break	1.7	%	ISO 527
Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	290	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-
Electrical properties			
ISO Data			
Surface resistivity	1000000	Ohm	IEC 62631-3-2
Other properties			
Density	1350	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	3	h	-
Processing humidity	≤0.02	%	-
Melt temperature	370 - 390	°C	-
Mold temperature	180 - 210	°C	-

Characteristics

Processing

Injection Molding

Features

Thermal Stability

Chemical Resistance

General Chemical Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa