

KEBAPEAK PEEK XF1720

PEEK-CF20

Barlog plastics GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	8000	MPa	ISO 527
Stress at break	130	MPa	ISO 527
Charpy impact strength, +23°C	140	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	320	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Volume resistivity	1E15	Ohm*m	IEC 62631-3-1
Other properties			
Humidity absorption	0.05	%	Sim. to ISO 62
Density	1430	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Features

Tribologic Grade

Applications

Aircraft and Aerospace, Automotive, Electrical and Electronical, Encapsulation, Medical

Regional Availability

Europe