

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	6.5	g/10min	ISO 1133
Temperature	360	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	15500	MPa	ISO 527
Tensile Strength	230	MPa	ISO 527
Strain at break	1.6	%	ISO 527
Charpy impact strength, +23°C	40	kJ/m <sup>2</sup>	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	143	°C	ISO 11357-1/-2

Electrical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Volume resistivity	59.7	Ohm*m	ISO 3915

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1350	kg/m <sup>3</sup>	ISO 1183
Bulk density	660	kg/m <sup>3</sup>	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	140 - 160	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	390 - 400	°C	-
Mold temperature	160 - 200	°C	-
Zone 1	360 - 400	°C	-

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets, Black

### Regional Availability

North America, Europe, Asia Pacific, South and Central America