

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
Thermal conductivity of melt	1	W/(m K)	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	22000	MPa	ISO 527
Stress at break	290	MPa	ISO 527
Strain at break	1.9	%	ISO 527
Flexural modulus, 23°C	20000	MPa	ISO 178
Flexural strength	400	MPa	ISO 178
Charpy impact strength, +23°C	60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	7.5	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	60	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	8.5	kJ/m ²	ISO 180/1A
Shore D hardness	86.5	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	143	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	347	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	5.5	E-6/K	ISO 11359-1/-2

Other properties	Value	Unit	Test Standard
Water absorption	0.4	%	Sim. to ISO 62
Density	1370	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	3 - 5	h	-
Processing humidity	≤0.02	%	-
Mold temperature	180 - 200	°C	-
Feed temperature	≤100	°C	-
Zone 1	365	°C	-
Zone 2	370	°C	-
Zone 3	375	°C	-
Zone 4	380	°C	-
Nozzle temperature	385	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Black

Features

Tribologic Grade

Chemical Resistance

General Chemical Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa