

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	34500 / 34500	MPa	ISO 527
Stress at break	245 / 240	MPa	ISO 527
Strain at break	1.1 / 1	%	ISO 527
Flexural modulus, 23°C	33000 / -	MPa	ISO 178
Flexural strength	365 / -	MPa	ISO 178
Charpy impact strength, +23°C	40 / 35	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6 / 6	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	342 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	280 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 8.00 MPa	250 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

Other properties	dry / cond	Unit	Test Standard
Density	1450 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	385	°C	-
Mold temperature	195	°C	-
Injection pressure	200	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

Black

Features

Tribologic Grade

Applications

Aircraft and Aerospace, Automotive, Medical

Regional Availability

Europe, Asia Pacific