

Product Texts

long fiber reinforced

Mechanical properties**ASTM Data**

	Value	Unit	Test Standard
Tensile Modulus	37880	MPa	ASTM D 638
Tensile Strength	218	MPa	ASTM D 638
Elongation at Yield	0.7	%	ASTM D 638
Flexural Modulus	25380	MPa	ASTM D 790
Flexural Strength	304	MPa	ASTM D 790
Izod Impact unnotched, 1/8 in	726	J/m	ASTM D 256

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Features

Long fiber reinforced

Regional Availability

North America, Europe, Asia Pacific