

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	8800 / -	MPa	ISO 527
Stress at break	165 / -	MPa	ISO 527
Strain at break	2.6 / -	%	ISO 527

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	342 / *	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn. Thickness tested	V-0 / *	class	IEC 60695-11-10
	1.6 / *	mm	-

Other properties	dry / cond	Unit	Test Standard
Density	1430 / -	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	385	°C	-
Mold temperature	195	°C	-
Injection pressure	200	MPa	-

## Characteristics

### Processing

Injection Molding

### Applications

Aircraft and Aerospace, Automotive, Medical

### Delivery form

Natural Color

### Regional Availability

Europe, Asia Pacific