

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	11800	MPa	ISO 527
Yield stress	180	MPa	ISO 527
Strain at break	7.6	%	ISO 527
Flexural modulus, 23°C	11300	MPa	ISO 178
Flexural strength	270	MPa	ISO 178
Charpy notched impact strength, +23°C	7.5	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	58	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	14.1	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	143	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	328	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	18	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Dissipation factor, 1MHz	30	E-4	IEC 62631-2-1
Electric strength	20	kV/mm	IEC 60243-1
<b>Other properties</b>			
Water absorption	0.3	%	Sim. to ISO 62
Density	1510	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding, Other Extrusion

### Regional Availability

Europe

### Delivery form

Pellets