

RTP 2299 X 115088 F

PEEK-GF35

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0025	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	12820	MPa	ASTM D 638
Tensile Strength	190	MPa	ASTM D 638
Flexural Modulus	12820	MPa	ASTM D 790
Flexural Strength	296	MPa	ASTM D 790
Izod Impact notched, 1/8 in	80.1	J/m	ASTM D 256

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E10	Ohm	ASTM D 257
Volume Resistivity	100000	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1580	kg/m ³	ASTM D 792
Moisture Content	0.1	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	3	h	-
Melt temperature	349 - 399	°C	-
Mold temperature	163 - 218	°C	-
Injection pressure	82.7 - 124	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific