

**RamOfin PL306G4NT**

PE-GF20

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>3</b>	g/10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>3000</b>	MPa	ISO 527
Tensile Strength	<b>45</b>	MPa	ISO 527
Strain at break	<b>9</b>	%	ISO 527
Flexural modulus, 23°C	<b>2600</b>	MPa	ISO 178
Flexural strength	<b>64</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>22</b>	kJ/m <sup>2</sup>	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	<b>1080</b>	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Mold temperature	<b>30 - 70</b>	°C	-
Feed temperature	<b>30 - 60</b>	°C	-
Zone 1	<b>190 - 210</b>	°C	-
Zone 2	<b>200 - 220</b>	°C	-
Zone 3	<b>210 - 230</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa