

RTP 2181 HEC HF

PEI-(CF+MED(Ni))10

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0015	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	7584	MPa	ASTM D 638
Tensile Strength	114	MPa	ASTM D 638
Flexural Modulus	6895	MPa	ASTM D 790
Flexural Strength	207	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257
Volume Resistivity	100	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1310	kg/m ³	ASTM D 792
Moisture Content	0.04	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	4	h	-
Melt temperature	366 - 399	°C	-
Mold temperature	141 - 177	°C	-
Injection pressure	82.7 - 124	MPa	-

Characteristics**Processing**

Injection Molding

Features

EMI Attenuation/Shielding

Special Characteristics

Increased electrical conductivity

Regional Availability

North America, Europe, Asia Pacific