

Product Texts

LNP STAT-KON EE004 compound is based on Polyetherimide (PEI) resin containing 20% carbon fiber. Added features of this grade include: Electrically Conductive.

UL Yellow Card Link [E45329-101282613](https://www.ul.com/yellow-card/E45329-101282613)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.2	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.4	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	14800	MPa	ISO 527
Stress at break	195	MPa	ISO 527
Strain at break	1.7	%	ISO 527
Flexural modulus	12300	MPa	ISO 178
Flexural strength	264	MPa	ISO 178
Izod impact strength, +23°C, 4mm	30	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	7	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Strength at Break	170	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Flexural Modulus	12330	MPa	ASTM D 790
Flexural Strength	259	MPa	ASTM D 790
Izod Impact notched, 1/8 in	58	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	534	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	212	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	217	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	10	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	47	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.5	mm	-
ASTM Data			
DTUL @ 264 psi	212	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257
Volume Resistivity	1000000	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1340	kg/m ³	ISO 1183
Density	1340	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	360 - 400	°C	-
Mold temperature	140 - 180	°C	-

LNP™ STAT-KON™ Compound EE004

PEI-CF20

Saudi Basic Industries Corporation (SABIC)

Zone 1	360 - 380	°C	-
Zone 2	370 - 390	°C	-
Zone 3	380 - 400	°C	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity