

Product Texts

LNP THERMOCOMP 9X99089 compound is based on Polyetherimide (PEI) resin containing 20% carbon fiber. Added features of this grade include: Electrically Conductive.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	11100	MPa	ISO 527
Stress at break	185	MPa	ISO 527
Strain at break	1.7	%	ISO 527
Flexural modulus	10900	MPa	ISO 178
Izod impact strength, +23°C, 4mm	40	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	6	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	213	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1340	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	360 - 365	°C	-
Mold temperature	120 - 150	°C	-
Zone 1	345 - 355	°C	-
Zone 2	355 - 365	°C	-
Zone 3	365 - 375	°C	-
Screw speed	60 - 100	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity