

Product Texts

Filler: 30 % Miscanthus

Processing/Physical Characteristics**Value****Unit****Test Standard****ISO Data**

Melt flow index, MFI

2.3

g/10min

ISO 1133

Temperature

190

°C

-

Load

2.16

kg

-

Mechanical properties**Value****Unit****Test Standard****ISO Data**

Tensile Modulus

3340

MPa

ISO 527

Strain at break

5.1

%

ISO 527

Charpy impact strength, +23°C

8.4kJ/m²

ISO 179/1eU

Characteristics**Processing**

Injection Molding

Applications

Packaging

Certifications

Contains renewable resources

Regional Availability

Europe