

Doill Wood Plastic 15

PE-W15

Doil Ecotec Co., Ltd.

Product Texts

3D Printing Filament from WPC.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.3	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.5	%	ISO 294-4, 2577

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	78	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1020	kg/m ³	ISO 1183

Characteristics

Processing

Blow Molding

Features

Low Odor

Certifications

Contains renewable resources

Regional Availability

Asia Pacific