

WPC BIO PE H50-500-20

PE-W50

Jelu-Werk Josef Ehrler GmbH & Co KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	4850	MPa	ISO 527
Tensile Strength	39	MPa	ISO 527
Flexural modulus, 23°C	3920	MPa	ISO 178

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183
Bulk density	550	kg/m ³	-

Characteristics**Processing**

Injection Molding

Certifications

Contains renewable resources

Delivery form

Pellets, Natural Color

Regional Availability

Europe