

Product Texts

Enhanced flow Polyetherimide (Tg 217C). ECO Conforming. US FDA and EU Food Contact compliant, NSF 51 listing. UL94 V0 and 5VA listing. Effective June 2007, this grade will no longer be supported with biocompatibility information and should not be used for medical applications which require biocompatibility. Alternative grade HU1110.

UL Yellow Card Link [E121562-101048269](https://www.ulprospector.com/1110F)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	16	g/10min	ASTM D 1238
Temperature	337	°C	-
Load	6.6	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	3720	MPa	ASTM D 638
Tensile Strength at Yield	110	MPa	ASTM D 638
Elongation at Break	70	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.4	mm	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	3.0	mm	-

Other properties	Value	Unit	Test Standard
Density	1360	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	350 - 400	°C	-
Mold temperature	135 - 165	°C	-
Zone 1	330 - 400	°C	-
Zone 2	340 - 400	°C	-
Zone 3	345 - 400	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America

Certifications

Food contact, Food approval FDA 21 CFR