

Hybrid S464LG

(PC+ABS)

Ravago Manufacturing Americas

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	14	cm ³ /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	15	g/10min	ASTM D 1238
Temperature	260	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Yield stress	52	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	2230	MPa	ISO 178
Izod notched impact strength, +23°C	37	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Strength at Yield	51.7	MPa	ASTM D 638
Elongation at Break	55	%	ASTM D 638
Flexural Modulus	2210	MPa	ASTM D 790
Izod Impact notched, 1/8 in	530	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	112	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 264 psi	110	°C	ASTM D 648
Other properties			
Density	1130	kg/m ³	ISO 1183
Density	1130	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Applications

Automotive, General Purpose

Delivery form

Pellets

Regional Availability

North America