

ULTEM™ Resin MD147 - Europe

PEI

Saudi Basic Industries Corporation (SABIC)

Product Texts

Transparent, high flow Polyetherimide (Tg 217C)

Processing/Physical Characteristics

ISO Data

	Value	Unit	Test Standard
Melt volume-flow rate, MVR	25	cm ³ /10min	ISO 1133
Temperature	360	°C	-
Load	5	kg	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Special Characteristics

Transparent