

Product Texts

High flow ULTEM for thin wall application

UL Yellow Card Link [E45587-101275405](https://www.ulprospector.com/asia/ulcard/E45587-101275405)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	70	cm ³ /10min	ISO 1133
Temperature	345	°C	-
Load	10	kg	-
ASTM Data			
Melt Flow Index, MFI	30	g/10min	ASTM D 1238
Temperature	337	°C	-
Load	6.6	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	142	MPa	ISO 527
Strain at break	2.4	%	ISO 527
Flexural modulus	7170	MPa	ISO 178
Izod notched impact strength, +23°C, 4mm	8	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	9400	MPa	ASTM D 638
Tensile Strength at Break	148	MPa	ASTM D 638
Elongation at Break	2.4	%	ASTM D 638
Flexural Modulus	7360	MPa	ASTM D 790
Izod Impact notched, 1/8 in	80	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
ASTM Data			
DTUL @ 264 psi	201	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1420	kg/m ³	ISO 1183
Density	1420	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	350 - 400	°C	-
Mold temperature	135 - 165	°C	-
Zone 1	330 - 400	°C	-
Zone 2	340 - 400	°C	-
Zone 3	345 - 400	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific