ULTEM™ Resin SF2350 - Europe

PEI-GF — Saudi Basic Industries Corporation (SABIC)

Product Texts

High flow ULTEM blends for thin wall application

UL Yellow Card Link E207780-100116344

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	**30**	cm³/10min	ISO 1133
Temperature	**345**	°C	-
Load	**10**	kg	-
ASTM Data			
Melt Flow Index, MFI	**14.7**	g/10min	ASTM D 1238
Temperature	**337**	°C	-
Load	**6.6**	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	**171**	MPa	ISO 527
Strain at break	**2.5**	%	ISO 527
Flexural modulus	**9400**	MPa	ISO 178
Izod notched impact strength, +23°C, 4mm	**10**	kJ/m²	ISO 180/1A
ASTM Data			
Tensile Modulus	**11600**	MPa	ASTM D 638
Tensile Strength at Break	**172**	MPa	ASTM D 638
Elongation at Break	**2.6**	%	ASTM D 638
Flexural Modulus	**9320**	MPa	ASTM D 790
Izod Impact notched, 1/8 in	**95**	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	**204**	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	**1520**	kg/m³	ISO 1183
Density	**1520**	kg/m³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**150**	°C	-
Pre-drying - Time	**4 - 6**	h	-
Processing humidity	**≤0.02**	%	-
Melt temperature	**350 - 400**	°C	-
Mold temperature	**135 - 165**	°C	-
Zone 1	**330 - 400**	°C	-
Zone 2	**340 - 400**	°C	-
Zone 3	**345 - 400**	°C	-
Screw speed	**40 - 70**	rpm	-
Back pressure	**0.3 - 0.7**	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.