

**Product Texts**

10% Glass fiber filled, enhanced flow Polyetherimide (Tg 217C) with internal mold release. ECO Conforming, UL94 V0 and 5VA listing.

UL Yellow Card Link [E45587-236982](https://www.ulprospector.com/usa/Products/2110R)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>11.5</b>	g/10min	ASTM D 1238
Temperature	<b>337</b>	°C	-
Load	<b>6.6</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	<b>4610</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>114</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>115</b>	MPa	ASTM D 638
Elongation at Break	<b>6</b>	%	ASTM D 638
Izod Impact notched, 1/8 in	<b>53</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>0.4</b>	mm	-

Other properties	Value	Unit	Test Standard
Density	<b>1340</b>	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>150</b>	°C	-
Pre-drying - Time	<b>4 - 6</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>350 - 400</b>	°C	-
Mold temperature	<b>135 - 165</b>	°C	-
Zone 1	<b>330 - 400</b>	°C	-
Zone 2	<b>340 - 400</b>	°C	-
Zone 3	<b>345 - 400</b>	°C	-
Screw speed	<b>40 - 70</b>	rpm	-
Back pressure	<b>0.3 - 0.7</b>	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

Asia Pacific

**Applications**

Automotive