

Product Texts

20% Glass fiber filled, standard flow Polyetherimide (Tg 217C). ECO Conforming, UL94 V0 and 5VA listing. NSF 51 listing, WRAS certification in recognized colors.

UL Yellow Card Link [E121562-502535](https://www.ul.com/yellow-card/E121562-502535)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	7	cm ³ /10min	ISO 1133
Temperature	360	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6800	MPa	ISO 527
Stress at break	140	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus	6500	MPa	ISO 178
Charpy impact strength, +23°C	35	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	35	kJ/m ²	ISO 179/1eU
Izod impact strength, +23°C, 4mm	30	kJ/m ²	ISO 180/1U
Izod impact strength, -30°C, 4mm	30	kJ/m ²	ISO 180/1U
Ball indentation hardness	150	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, A	223	°C	ISO 306
Vicat softening temperature, B	212	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	218	°C	ISO 306
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.4	mm	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	1.9	mm	-
Thermal Conductivity	0.28	W/(m K)	DIN 52616
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (3)	3.2	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3	-	IEC 62631-2-1
Dissipation factor, 1MHz	25	E-4	IEC 62631-2-1
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	34	kV/mm	IEC 60243-1
Comparative tracking index	150	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	1	%	Sim. to ISO 62
Humidity absorption	0.55	%	Sim. to ISO 62
Density	1420	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	370 - 410	°C	-
Mold temperature	140 - 180	°C	-
Feed temperature	80 - 120	°C	-

ULTEM™ Resin 2200 - Europe

PEI-GF20

Saudi Basic Industries Corporation (SABIC)

Zone 1	350 - 400	°C	-
Zone 2	360 - 410	°C	-
Zone 3	370 - 420	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Applications

Automotive