

Product Texts

20% Glass fiber filled, high flow Polyetherimide (Tg 217C) with internal mold release and enhanced electroplatability. ECO Conforming, UL94 V0 and 5VA listing.

UL Yellow Card Link [E121562-221096](https://www.ulprospector.com/usa/Products/2210EPR)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	13	g/10min	ASTM D 1238
Temperature	337	°C	-
Load	6.6	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	6890	MPa	ASTM D 638
Tensile Strength at Yield	137	MPa	ASTM D 638
Tensile Strength at Break	137	MPa	ASTM D 638
Elongation at Yield	3	%	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	6890	MPa	ASTM D 790
Izod Impact notched, 1/8 in	80	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	587	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.4	mm	-
ASTM Data			
DTUL @ 66 psi	211	°C	ASTM D 648
DTUL @ 264 psi	206	°C	ASTM D 648
Vicat Temperature	210	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1390	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	350 - 400	°C	-
Mold temperature	135 - 165	°C	-
Zone 1	330 - 400	°C	-
Zone 2	340 - 400	°C	-
Zone 3	345 - 400	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America