ULTEM™ Resin CRS5201 - Asia

PEI-GF20 Saudi Basic Industries Corporation (SABIC)

Product Texts

20% Glass fiber filled, standard flow Polyetherimide copolymer (Tg 225C) with enhanced chemical resistance to strong acids, bases, aromatics, and ketones. ECO Conforming, UL94 V0 and 5VA listing.

UL Yellow Card Link E121562-221118

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	**2.3**	g/10min	ASTM D 1238
Temperature	**337**	°C	-
Load	**6.6**	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	**6890**	MPa	ASTM D 638
Tensile Strength at Break	**131**	MPa	ASTM D 638
Elongation at Break	**5**	%	ASTM D 638
Izod Impact notched, 1/8 in	**74**	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	**V-0**	class	IEC 60695-11-10
Thickness tested	**1.5**	mm	-
Burning behav. 5V at thickness h	**5VA**	class	IEC 60695-11-20
Thickness tested	**1.5**	mm	-

Other properties	Value	Unit	Test Standard
Density	**1420**	kg/m³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**150**	°C	-
Pre-drying - Time	**4 - 6**	h	-
Processing humidity	**≤0.02**	%	-
Melt temperature	**365 - 390**	°C	-
Mold temperature	**135 - 165**	°C	-
Zone 1	**345 - 365**	°C	-
Zone 2	**355 - 375**	°C	-
Zone 3	**365 - 390**	°C	-
Screw speed	**40 - 70**	rpm	-
Back pressure	**0.3 - 0.7**	MPa	-

Characteristics

Processing
Injection Molding

Applications
Automotive

Chemical Resistance
General Chemical Resistance

Regional Availability
Asia Pacific

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.