

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>20</b>	g/10min	ASTM D 1238
Temperature	<b>350</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Melting Temperature	<b>302</b>	°C	ASTM D 3418
<b>Other properties</b>			
Density	<b>1390</b>	kg/m <sup>3</sup>	ASTM D 792
Bulk Density	<b>500</b>	kg/m <sup>3</sup>	-

### Characteristics

#### Processing

Additive Manufacturing, Laser Sintering

#### Delivery form

Powder

#### Special Characteristics

Flame retardant

#### Chemical Resistance

General Chemical Resistance

#### Applications

Aircraft and Aerospace, Automotive

#### Regional Availability

North America, Europe, Asia Pacific