

Product Texts

Rynite® FR335 NC010 is a 35% glass/mineral reinforced, flame retardant, modified polyethylene terephthalate resin.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	12300	MPa	ISO 527
^[C] Stress at break	130	MPa	ISO 527
^[C] Strain at break	1.9	%	ISO 527
^[C] Charpy impact strength, +23°C	30	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	9	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	248	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	236	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	18	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	64	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	36	kV/mm	IEC 60243-1
^[C] Comparative tracking index	300	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1670	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific, South and Central America