

Product Texts

Common features of Rynite® thermoplastic polyester include mechanical and physical properties such as excellent balance of strength and stiffness, dimensional stability, creep resistance, heat resistance, high surface gloss and good inherent electrical properties at elevated temperature. It can be processed over a broad temperature range and has excellent flow properties.

Rynite® thermoplastic polyester resins are typically used in demanding applications in the automotive, electrical and electronics, appliances where they successfully replace metals and thermosets, as well as other thermoplastic polymers.

Rynite® 940 BK505 is a 40% mica/glass reinforced modified polyethylene terephthalate resin with low warpage, high stiffness and strength, and excellent electrical properties.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
^[C] Ejection temperature	170	°C	-
ASTM Data			
Mold Shrinkage, MD	0.0017	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0055	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	12500	MPa	ISO 527
^[C] Stress at break	110	MPa	ISO 527
^[C] Strain at break	1.8	%	ISO 527
^[C] Charpy impact strength, +23°C	35	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Modulus	11600	MPa	ASTM D 638
Tensile Strength	117	MPa	ASTM D 638
Elongation at Break	1.9	%	ASTM D 638
Compressive Strength	175	MPa	ASTM D 695
Flexural Modulus	11700	MPa	ASTM D 790
Flexural Strength	198	MPa	ASTM D 790
Rockwell Hardness	R 115	-	ASTM D 785
Izod Impact notched, 1/8 in	75	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	69	J/m	ASTM D 256
Temperature	-40	°C	-
Izod Impact unnotched, 1/8 in	530	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	250	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	220	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	241	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	15	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	60	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-
Coefficient of Thermal Expansion, MD	24	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	60	E-6/K	ASTM D 696
DTUL @ 66 psi	241	°C	ASTM D 648

Rynite® 940 BK505

PET-(GF+P)40

Celanese

DTUL @ 264 psi	211	°C	ASTM D 648
Melting Temperature	250	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	4.2	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.9	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	70	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	146	E-4	IEC 62631-2-1
^[C] Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	1E14	Ohm	IEC 62631-3-2
^[C] Electric strength	33	kV/mm	IEC 60243-1
^[C] Comparative tracking index	250	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	23	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.015	-	ASTM D 150
Dielectric Constant, 1 MHz	3.7	-	ASTM D 150
Surface Resistivity	1E14	Ohm	ASTM D 257
Volume Resistivity	1E15	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1640	kg/m ³	ISO 1183
Water Absorption, 24hr	0.05	%	ASTM D 570
Density	1640	kg/m ³	ASTM D 792

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Additives

Release agent

Special Characteristics

Heat stabilized or stable to heat

Features

Low Warpage, Thermal Stability, Weldable

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa