

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>13</b>	g/10min	ASTM D 1238
Mold Shrinkage, MD	<b>0.006</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>1700</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>59</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>58</b>	MPa	ASTM D 638
Elongation at Yield	<b>86</b>	%	ASTM D 638
Elongation at Break	<b>150</b>	%	ASTM D 638
Flexural Modulus	<b>2500</b>	MPa	ASTM D 790
Flexural Strength	<b>87</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 118</b>	-	ASTM D 785

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>127</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>106</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1220</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Regional Availability**

North America