

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	1700	MPa	ASTM D 638
Tensile Strength at Yield	59	MPa	ASTM D 638
Tensile Strength at Break	60	MPa	ASTM D 638
Elongation at Yield	68	%	ASTM D 638
Elongation at Break	150	%	ASTM D 638
Flexural Modulus	2500	MPa	ASTM D 790
Flexural Strength	88	MPa	ASTM D 790
Rockwell Hardness	R 116	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	126	°C	ASTM D 648
DTUL @ 264 psi	107	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1210	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Regional Availability

North America